




FOAMGLAS® READY BLOCK TAPERED T4+

Page: 1

Date: 01.02.2015

Supersedes: 01.12.13

www.foamglas.com



FOAMGLAS® READY BLOCK TAPERED T4+ consists of FOAMGLAS® READY BLOCK T4+ slabs which are tapered across their width, or sometimes their length. A central arrow stamped onto the top surface indicates the direction of fall.

The upper surface is covered with a bitumen coating. It allows for direct torch-on of waterproofing sheets.

Form of delivery

length x width [mm]	600 x 450							
average thickness [mm]	60	70	80	90	100	110	120	130
length x width [mm]	600 x 450							
average thickness [mm]	140	150	160	170	180	190	200	

Standard angles of inclination:

1.1%, 1.3%, 1.7%, 2.0%, 2.8%, 3.0%, 3.3%, 4.0%, 4.4%, 5.0%, 5.6%, 6.7%.


Other dimensions and thicknesses are available on request.

General FOAMGLAS® Cellular Glass Insulation characteristics


- Description : FOAMGLAS® Insulation is manufactured from specially graded recycled glass (≥ 60%) and natural raw materials which are available in abundant supply (sand, dolomite, lime...). The insulation is totally inorganic, contains no ozone depleting propellants, flame resistant additives or binders. Without VOC or other volatile substances.
- Reaction to fire (EN 13501-1) : Material complying with Euroclass A1, non-combustible, no toxic fumes
- Service temperature limits : from -265°C to +430°C
- Water vapour resistance (EN ISO 10456) : $\mu = \infty$
- Hygroscopicity : zero
- Capillarity : zero
- Melting point (cf DIN 4102-17) : >1000 °C
- Thermal expansion coefficient (EN 13471) : $9 \times 10^{-6} \text{ K}^{-1}$
- Specific heat (EN ISO 10456) : 1000 J/(kg·K)
- FOAMGLAS® characteristics :



Waterproof




Resistant to attack



High compressive strength




Acid resistant / chemical resistant




Easy cut to shape



Non-combustible




Impervious to water vapour



Dimensionally stable



Ecological



Radon protection



FOAMGLAS® READY BLOCK TAPERED T4+

Page: 2

Date: 01.02.2015

Supersedes: 01.12.13

www.foamglas.com

1. Product characteristics according to EN 13167 ¹⁾

Density (± 10%) (EN 1602)	: 115 kg/m ³
Thickness, average (EN 823) ± 2 mm	: from 60 to 200 mm
Length (EN 822) ± 2 mm	: 600 mm
Width (EN 822) ± 2 mm	: 450 mm
Thermal conductivity (EN ISO 10456)	: $\lambda_D \leq 0,041$ W/(m·K)
Reaction to fire (EN 13501-1)	: Euroclass A1
Point load (EN 12430)	: PL $\leq 1,5$ mm
Compressive strength (EN 826 annexe A)	: CS ≥ 600 kPa
Bending strength (EN 12089)	: BS ≥ 450 kPa
Tensile strength (EN 1607)	: TR ≥ 150 kPa

1) CE-marking ensures conformity with the mandatory essential requirements of CPD as mentioned in EN 13167; within the CEN Keymark certification all mentioned characteristics are certified by an empowered, notified and accredited 3rd party.

2. Additional product characteristics

Thermal diffusivity at 0°C	: 4.2×10^{-7} m ² /sec
BRE Green Guide Rating	: A

3. Applications

READY BLOCK TAPERED ROOF SYSTEM, cut-to-falls insulation system:

- flat roofs (cold bonding on concrete using PC[®] 500)
- metal and special roofs
- belowgrade floors and walls
- interior insulation, floors

Insulation system allowing for torch-on roofing.