

This test report replaces the test report EUFI29-23000306-T5 dated in 20 January 2023. Changes in structure of the specimen, definition of the substrate and additional deviation.

Determination of external fire exposure to roofing of FATRAFOL 810/V (1,2 mm) according to CEN TS 1187:2012, Test 2

Requested by Bestor Group AS
Taavi Ossip
Valdeku 168
EE-11217 Tallinn
taavi.ossip@bestor.ee

Order ref. M7RGPT220099-02

Contact person Eurofins Expert Services Oy
Taru Huokuniemi
Kivimiehentie 4
FI-02150 Espoo, Finland
taruhuokuniemi@eurofins.fi

Products The customer gave the following information about the products:

Top layer

- Product name: FATRAFOL 810/V (1,2 mm)
- Product description: roofing membrane on the basis of PVC-P reinforced with a polyester grid
- Nominal mass per unit area: 1430 g/m²
- Thickness: 1,2 mm
- Manufacturer: Fatra, a.s., třída Tomáše Bati 1541, 763 61 Napajedla, Česká republika

Mineral wool insulation board

- Product name: PAROC ROS 50
- Thickness: 50 mm
- Manufacturer: Paroc Group, Energiakuja 3, FI-00180 Helsinki, Finland

Polyethylene foil (PE foil), vapour control barrier

- Product name: fatrapar 200
- Nominal thickness: 0,2 mm
- Manufacturer: PYTLÍK, a.s., IČ: 26459990, Bečovská1326/9, 104 00 Praha 10 – Uhřetěves, Česká republika

Samples

The sample of the products was chosen by the customer.

Date of delivery: 20 January.2023

Top layer

Thickness: 1,2 mm

Nominal mass per unit area: 1430 kg/m² (controlled by EES)

Mineral wool

Thickness: 50 mm

Nominal density: 122 kg/m³ (controlled by EES)

PE-foil

Thickness: 0,2 mm

Nominal density: 149 g/m² (controlled by EES)

Wood particle board substrate

Thickness: 18 mm

Nominal density: 581 kg/m³ (controlled by EES)

Date of delivery: 27 April 2023

Top layer

Thickness: 1,2 mm

Nominal mass per unit area: 1500 kg/m²

Mineral wool

Thickness: 50 mm

Nominal density: 143 kg/m³ (controlled by EES)

PE-foil

Thickness: 0,2 mm

Nominal density: 150 g/m² (controlled by EES)

Samples were controlled by Eurofins Expert Service

Test specimens	<p>Eight test specimens were made by the customer with dimensions of 400 mm x 1000 mm</p> <p>Structure of the specimens from substrate to top layer:</p> <ul style="list-style-type: none"> – wooden particle board, mechanically attached – PE foil, mechanically attached – mineral wool, mechanically attached – FATRAFOL 810/V (1,2mm)
Date of test	1 February 2023, 6 May 2023
Test method	<p>CEN TS 1187:2012, Test methods for external exposure to roofs - Test 2: Method with burning brands and wind.</p> <p>A description of the test method and the classification criteria of $B_{ROOF}(t_2)$ given in the classification standard EN 13501-5:2016 and concerning Test 2 are presented in Appendix 1</p>
Test results	Test results are presented in Appendix 2
Deviation	Full test serie have been tested with the wood particle board as a substrate with density 581 kg/m^3 . Two additional test with standard wood particle board as a substrate were made. The deviation in substrate densities did not have an influence on the final result.
Note	<p>The results relate to the behaviour of the test specimen of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.</p> <p>Eurofins Expert Services Oy is a notified body 0809 concerning the Construction Products Regulation (CPR).</p> <p>Espoo, 8 May 2023</p> <p>Taru Huokuniemi <i>Senior Expert</i></p>
Appendices	<p>Appendix 1, Description of the test method and the classification criteria of $B_{ROOF}(t_2)$</p> <p>Appendix 2, Test results</p>
Distribution	Customer Electronically approved

DESCRIPTION OF THE METHOD

CEN TS 1187:2012 *Test methods for external fire exposure to roofs*

Test 2: *Method with burning brands and wind*

Test specimens

The size of test specimens are 400 mm x 1000 mm and number of specimens is six.

Test specimens are normally prepared by attaching the product to a standard substrate. The specimen may also be tested on a non-standard substrate, in which case the test results are valid for that substrate only.

The standard combustible substrates are:

wood particle board, density $(680 \pm 50) \text{ kg/m}^3$, thickness $(19 \pm 2) \text{ mm}$

expanded polystyrene (EPS) (not fire retarded treated), density $(20 \pm 5) \text{ kg/m}^3$, $(50 \pm 10) \text{ mm}$

The standard non-combustible substrates are:

fibre reinforced calcium silicate board, density $(680 \pm 50) \text{ kg/m}^3$, $(10 \pm 2) \text{ mm}$

mineral wool, density $(150 \pm 20) \text{ kg/m}^3$, thickness $(50 \pm 10) \text{ mm}$

The test specimens are conditioned prior the tests to constant mass in a room with a temperature of $23 \pm 2 \text{ }^\circ\text{C}$ and relative humidity of $50 \pm 5 \text{ \% RH}$.

Test procedure

The test specimen is mounted in the test apparatus at an angle of 30° to the horizontal plane. A burning wooden crib (100 mm x 100 mm, 40 g) is placed on the test specimen with its centre 100 mm from the bottom edge of the specimen. Three tests are performed with air velocities along the specimen of 2 m/s and 4 m/s respectively.

During the tests the time at which the test specimen ignites, the time at which the flames die out, the time at which the glow dies out and the behaviour of the test specimen are observed and recorded.

The test is terminated by extinguishing of the fire on the specimen 15 min after the start of the test or when the flame front has reached the upper end of the specimen. After the test the test specimen is examined and the extent of damages done to both the roof covering and the substrate are measured.

CLASSIFICATION CRITERIA – $B_{\text{ROOF}}(t_2)$

The classification criteria are given in the classification standard EN 13501-5:2016 "*Fire classification of construction products and building elements - Part 5: Classification using test data from external fire exposure to roof tests*".

Classification parameters of Test 2 are mean damaged length and maximum damaged length of the roof covering and the substrate. Classification criteria of $B_{\text{ROOF}}(t_2)$ for both test series at 2 m/s and 4 m/s wind speed are

- mean length of damage in the roof covering and substrate $\leq 0,550 \text{ m}$
- maximum length of damage in the roof covering and the substrate $\leq 0,800 \text{ m}$

VALIDITY OF CLASSIFICATION

Depending on quality and density of the substrate used in tests the classification is valid for

- non-combustible substrates with density of at least 0,75 times the density of the substrate used in tests
- combustible and non-combustible substrate with density of at least 0,75 times the density of the substrate used in tests

6.9.2018

TEST RESULTS

Test method: CEN TS 1187:2012, Test 2
Product: FATRAFOL 810/V (1,2 mm)
Substrate: Wood particle board (density 581 kg/m³)

Table 1. Test results *FATRAFOL 810/V(1,2 mm) + mineral wool + PE-foil+ wood particle board*

Wind velocity	2 m/s				4 m/s			
Test No.	1	2	3	Mean	1	2	3	Mean
Covering ignited, min:s	00:13	00:14	00:13	00:13	00:13	00:14	00:13	00:13
Flames extinguished, min:s	03:40	02:34	03:12	03:09	02:49	02:28	03:20	02:52
Glowing ended, min:s	10:46	11:14	10:34	10:51	08:19	08:26	08:43	08:29
Length of damage in membrane, mm*	436	397	452	428	468	463	493	475
Length of damage in substrate, mm*	0	0	0	0	0	0	0	0

*) Measured from the middle of the ignition source

TEST RESULTS

Test method: CEN TS 1187:2012, Test 2

Product: FATRAFOL 810/V (1,2 mm)

Substrate: Standard wood particle board (density $680 \text{ kg/m}^3 \pm 50 \text{ kg}$)

Table 1. Test results *FATRAFOL 810/V(1,2 mm) + mineral wool + PE-foil+ standard wood particle board*

Wind velocity	2 m/s				4 m/s			
Test No.	1	2	3	Mean	1	2	3	Mean
Covering ignited, min:s	0:13			0:13	0:13			0:13
Flames extinguished, min:s	3:59			3:59	2:47			2:47
Glowing ended, min:s	13:59			13:59	9:09			9:09
Length of damage in membrane, mm*	460			460	466			466
Length of damage in substrate, mm*	0			0	0			0

*) Measured from the middle of the ignition source