


ISOFOAM IF 2 mm

Product:	ISOFOAM IF 2 mm	
Supplier:	MASTERPLAST International Kft., 8143 Sárszentmihály, Árpád u. 1/a. (www.masterplastinternational.com)	
Size, packaging:	1 m × 50 m = 50m ² /roll (or customized for customer's request)	
Application:	Levels the slight unevenness of the properly dry base and reduces the unpleasant effect of the impact-sound under laminate and parquet floorings in rooms in case of low frequentation, moderate load-bearing and normal acoustic requirements. Lay on the base surface without overlapping, before flooring.	
Material:	Extruded, non-cross-linked and closed cell Polyethylene (LD-PE)	

Properties	Relevant standards	Technical data
Thickness	EN 823	2 (±)0,3 mm
Length	EN 822	nominal (±)1%
Width	EN 822	100 cm (±)1%
Mass per unit area	EN 1602	40 g/m ² (±)10%
Density	EN 1602	21 kg/m ³ (±)5%
Tensile strength (on a 50mm wide sample)	EN 12311-2	65 N/5cm / 45 N/5cm
Elongation (on a 50mm wide sample)	EN 12311-2	95% / 95%
Compression strength (compression of 10%; 25%; 50%)	EN 826	min 3,5 kPa / min 20 kPa / min 55 kPa
Thermal conductivity (λ)	EN 12667	0,050 W/m.K
Impact sound insulation, ΔL _w (under 7mm-thick laminate, on 14cm-thick reinforced concrete slab)	EN 140-8	19 dB
Water vapour resistance factor (μ)	EN ISO 12572	~3650
Water vapour diffusion-equivalent air layer thickness (S _d)	EN ISO 12572	~7 m
Reaction to fire	EN 13501-1	F
Temperature resistance		(-)30°C - (+)70°C

Storage and handling

Under dry conditions, protected against atmospheric exposure, especially sun-radiation and other heat sources as well as against moisture and rain. Depending on the environmental conditions - temperature, ventilation -, within some days after the production, small amounts of isobutan - used during the production - is released from the foam, that are heavier than air and concentrates at ground level, so proper ventilation is necessary during storage and transportation. Isobutane is highly inflammable, it must be kept away from ignition source and avoid electrostatical discharges!

Guarantee, warranty

In accordance with the current legislations and the conditions of the distributor. The observation of the application rules of the product and presentation of the invoice constitute a prerequisite for possible future warranty claims.

Standards, specifications

ÉME (Hungarian Technical Approval) A-128/2011

Health and safety

No labelling required in accordance with the relevant regulation (EC) No. 1907/2006 of the European Parliament and of the Council.

This datasheet corresponds to our current knowledge, experiences and general informations on the subject, but may be revised as new knowledge and/or experience becomes available. It does not imply any legally binding assurance. The product possesses the given technical characteristics. Since all variations of end-using of the product can not be anticipated, the designer/end-user's responsibility to make sure of the suitability of this product for particular purposes, structures. The manufacturer supposes essential technical skill and skillfull application during construction.

This technical datasheet is applied to products sold by Masterplast International Kft. and valid until withdrawal or until modification. Since this datasheet may be subject to revision, it is the responsibility of designer/end-user to make sure of possessing the latest version of the datasheet (*see date of issuing). Most recent version of this datasheet can be also accessed under www.masterplastinternational.com. Herewith the previously issued versions of this datasheets lose their validity and must be replaced by this version!