## Test Report No. 7191058019 - MEC13/02A - TYK dated 30 Aug 2013



**Note:** This report is issued subject to the Testing and Certification Regulations of the TÜV SÜD Group and the General Terms and Conditions of Business of TÜV SÜD PSB Pte Ltd. In addition, this report is governed by the terms set out within this report.

## **Thermal Conductivity Test**

Tested for:

Everest Industries Limited The Genesis, A-32 Mohan Cooperative Industrial Estate Mathura Road 110048 New Delhi India

## Attn : Mr. Jasmit Singh

Description of sample:	Two pieces of <b>Insulation Material</b> of nominal size 300 mm (L) x 300 mm (W) x 10 mm (TK) were submitted on 23 <sup>rd</sup> July 2013.		
Sample Description:	Fibre Cement Board / MULTIPURPOSE FIBRE CEMENT BOARD		
Test standard:	1) ASTM C518 : 2010 Standard test method for steady-state thermal transmission properties by means of the heat flow meter.		
	<ol> <li>The thermal conductivity of material was measured by using a heat flow meter calibrated with standard fibreglass sample of thickness of 25mm</li> </ol>		
TEST RESULTS:			

Test Thermal conductivity test a. Dimension of specimen		Unit	Sample : Fibre Cement Board / MULTIPURPOSE FIBRE CEMENT BOARD
		mm	300 (L) x 300 (W) x 9.47 (TK)
b. Density		kg/m <sup>3</sup>	1364.45
c. Temperature	of hot face	°C	34.62
d. Temperature	of cold face	°C	15.08
e. Mean temper	ature	°C	24.85
f. Thermal cond	ductivity	W/mK (Kcal/mhK)	0.0872 0.0749

\* 1 W/mK = 0.859845 Kcal/mhK

hans.

Aldohny.



Laboratory: TÜV SÜD PSB Pte. Ltd. No.1 Science Park Drive Singapore 118221 Phone : +65-6885 1333 Fax : +65-6776 8670 E-mail: testing@tuv-sud-psb.sg www.tuv-sud-psb.sg Co. Reg : 199002667R

Regional Head Office: TÜV SÜD Asia Pacific Pte. Ltd. 3 Science Park Drive, #04-01/05 The Franklin, Singapore 118223





## APPENDIX:



Photo 1: Sample as received, Side 1



Photo 2: Sample as received, Side 2



Wan

Fabien Tan Associate Engineer

aldeh.

Chua Peck Cheong Product Manager Green Product Mechanical Centre



Please note that this Report is issued under the following terms :

- 1. This report applies to the sample of the specific product/equipment given at the time of its testing/calibration. The results are not used to indicate or imply that they are applicable to other similar items. In addition, such results must not be used to indicate or imply that TÜV SÜD PSB approves, recommends or endorses the manufacturer, supplier or user of such product/equipment, or that TÜV SÜD PSB in any way "guarantees" the later performance of the product/equipment. Unless otherwise stated in this report, no tests were conducted to determine long term effects of using the specific product/equipment.
- The sample/s mentioned in this report is/are submitted/supplied/manufactured by the Client. TÜV SÜD PSB therefore assumes no responsibility for the accuracy of information on the brand name, model number, origin of manufacture, consignment or any information supplied.
- 3. Nothing in this report shall be interpreted to mean that TÜV SÜD PSB has verified or ascertained any endorsement or marks from any other testing authority or bodies that may be found on that sample.
- 4. This report shall not be reproduced wholly or in parts and no reference shall be made by the Client to TÜV SÜD PSB or to the report or results furnished by TÜV SÜD PSB in any advertisements or sales promotion.
- 5. Unless otherwise stated, the tests were carried out in TÜV SÜD PSB Pte Ltd, No.1 Science Park Drive Singapore 118221.



July 2011